



Solumer™ 881 Polyolefin Elastomer

Introduction

Solumer[™] 881 is an **ethylene-octene copolymer** produced via Nexlene[™] technology. Solumer[™] 881 performs well in a wide range of general purpose thermoplastic elastomer applications and has excellent flow characteristics.

Applications

- General purpose thermoplastic elastomers
- Wire and cable

- Impact modification
- Footwear

Properties

			Typical Values	Unit	Test Method
Physical	Density		0.880	g/cm ³	ASTM D792
Properties	Melt index (2.16 kg @190°C)		1.0	g/10min	ASTM D1238
	Mooney viscosity (ML1+4 @ 121°C)		21	MU	ASTM D1646
Mechanical	Tensile strength at break		150	kgf/cm ²	ASTM D638 ²
Properties ¹	Elongation at break		800	%	ASTM D638 ²
	Tensile modulus (100% Elongation)		40	kgf/cm ²	ASTM D638 ²
	Flexural modulus (1% secant)		250	kgf/cm ²	ASTM D790
	Tear strength (Type C)		54	kgf/cm ²	ASTM D624
	Hardness	Shore A (1 sec)	79		ASTM D2240
		Shore D (1 sec)	25		ASTM D2240
Thermal	Melting temperature		68	°C	SK Method
Properties	Glass transition temperature		-49	°C	SK Method

¹ Evaluated using compression molded sample

Notes

These are *typical values* and are *not be construed as specifications*. The physical properties are highly dependent on the manufacturing conditions. So customers should confirm performances by their own tests.

For additional sales, order and technical assistance

Head office SK Global Chemical Co.,LTD

26 Jong-ro, Jongno-gu, Seoul, Korea TEL +82-2-2121-6757 **TS&D** SK innovation Global Technology 325 Exporo, Yueseong-gu, Daejeon, Korea

TEL +82-42-609-8623

² Crosshead speed: 500 mm/min